

Technical Data Sheet

EPOXY GROUT FILM REMOVER



Description

Epoxy Grout Film Remover is a unique product designed for the removal of epoxy grout film from tile, concrete and stone surfaces. It will eliminate most residue left behind after an epoxy grout Film Remover has been used. In addition, Epoxy Grout Film Remover will remove a variety of epoxies, acrylic, shellac, varnish and lacquer. Due to the differences of each material, several inconspicuous test patches should be completed to assure maximum performance. User must determine suitability of the product for their intended use.

To Remove Epoxy Grout Residue From

Ceramic Tile
Porcelain Tile
Natural Stone
Concrete

Special Features

Low Odor
Rinses With Water
Fast Acting
No Methylene Chloride



Coverage

Will vary depending on density, porosity, texture, surface absorption, weather, time solution left on surface and application methods. Epoxy Grout Film Remover will cover approximately 10-50 sqft per litre.



Instruction for Use

Small Areas or Spots: Apply Epoxy Grout Film Remover to the surface with a paint brush. Try to avoid getting on the grout joint. Allow to remain on the surface for 20 - 30 minutes and check repeatedly for softening of the cured epoxy film. You may need to allow for a longer cure time depending on how long film was down for and amount of film left on the surface. Allow to remain on the surface until the epoxy film is easily loosened. Remove Epoxy Grout Film Remover and residual epoxy film using a stiff-bristled brush (not steel wire) or coarse nylon scrubbing pad. Multiple applications may be necessary for more difficult situations. After removing residue, scrub the surface with a nylon pad and a solution of Tile & Stone Cleaner. Remove cleaning solution with a wet vacuum. Rinse with clean water after use and allow to dry.

Large Areas - Floors: Pour directly onto the surface and spread liberally with a brush or lamb's wool applicator. Work small areas approximately 3 feet wide. Avoid stepping into the solution. Allow to sit on the surface 15-30 minutes and agitate with a stiff brush. Begin checking for softening of the epoxy film every 5 minutes. Once the epoxy film has softened, remove it and the Epoxy Grout Film Remover with a wet vacuum, clean towels or mops. Multiple applications may be necessary. After removing residue, scrub the entire surface with a nylon brush or pad and a solution of Finish Sealer Stripper. Remove the cleaning solution with a wet vacuum. Rinse with clean water where necessary and allow to dry.

MADE IN INDIA

Technical Data Sheet



Packaging

Available in 1000ml bottles.



Storage

Store the product in a cool & dry place. Do not allow to freeze.



Technical Support

For additional technical support, contact Surie Porex Industries Pvt. Ltd.
Phone- 011-40776777



Additional Products

The main products manufactured by Surie Porex are Diamond Pads, Diamond Abrasives, Silicon Carbide Abrasives, Floor Polishing Machines, Stone Glues, Epoxy Resins, Polyester Resins Penetrating Sealers, Densifiers, Hardeners, Waxes and Cleaners for laying, polishing and maintenance of marble, granite, concrete and terrazzo.



Disclaimer

The information above reflects our latest technical know-how and is the outcome of ongoing laboratory research and testing. However, some factors are beyond our control. It is essential to integrate our suggestions with your own on-site preliminary tests and check.

Surie Porex accepts no liability for improper use of its products.